



Made in the
United States of America

A. MATERIAL: 15% Glass Filled Supertough Nylon

B. The hygroscopic (readily accepts moisture) properties of Nylon will make this tool suitable for use around ESD sensitive components after a few minutes of handling the tool with bare hands. If used with gloves in a clean environment the tools must be dipped in a topical antistatic solution before use in sensitive areas. Topical treatment should be repeated at six month intervals. Without exposure to moisture or antistatic treatment, Nylon is in the insulative resistance range and charges will not be removed to ground.

C. Notch for hooking and pulling wires or components.

D. Flat "screwdriver" surface for spudgng wire leads down flat on circuit boards.

E. Pointed end for forming wire leads or for use as pointer probe for holding objects for soldering.

F. Date Code (R=2006, S= 2007, T=2008, etc.)

Melting Point: 450° F (232° C)

Specifications and procedures subject to change without notice.

MENDA

PROBER, SOLDERING TOOL, NYLON

3651 WALNUT AVE., CHINO, CA 91710
PHONE: (909) 627-2453 FAX: (951) 755-8848
WEBSITE: MendaPump.com

DRAWING NUMBER
35622

DATE:
April
2011